



## Miragrid<sup>®</sup> 3XT

Miragrid<sup>®</sup> 3XT geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Miragrid<sup>®</sup> 3XT geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
			Machine Direction
Tensile Strength (at ultimate)	ASTM D6637	lbs/ft (kN/m)	3500 (51.1)
Tensile Strength (at 5% strain)	ASTM D6637	lbs/ft (kN/m)	1056 (15.4)
Creep Reduced Strength	ASTM D5262	lbs/ft (kN/m)	2215 (32.3)
Long Term Allowable Design Load <sup>1</sup>	GRI GG-4(b)	lbs/ft (kN/m)	1918 (28.0)

<sup>1</sup> NOTE: Long Term Allowable Design values are for sand, silt and clay

Physical Properties	Unit	Typical Value
Mass/Unit Area (ASTM D5261)	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	8.2 (278)
Roll Dimensions (width x length)	ft (m)	12 x 150 (3.6 x 46)
Roll Area	yd <sup>2</sup> (m <sup>2</sup> )	200 (165)
Estimated Roll Weight	lbs (kg)	119 (54)

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2012 TenCate Geosynthetics Americas  
Miragrid<sup>®</sup> is a registered trademark of Nicolon Corporation

